

PRODUCT DATA SHEET

GripEpoxy 116

Shutterboard Repair Epoxy Paste

Product Description:

Solvent free epoxy adhesive used to repair wooden shutters where a quick set is required.

Applications:

Rapid repairing defects on wooden shutterboards.

Advantages:

- Easy application
- Excellent adhesion to wooden shutters.

Typical Properties:

Mixing Ratio:	2 : 1
Pot Life:	10 - 15 minutes
Set:	1-2 Hour at 25°C
Compression:	> 50 MPa
Application Temperature:	10°C to 35°C
Colour:	Black

Yield:

Applied @ 1mm thick (1lt covers 1m²)

Packaging:

Supplied in 2kg kits

Shelf Life:

One year in original unopened containers.

Storage:

Store in a dry cool place

Placement Guidelines:

- Prepare the surface prior to application by removing all loose material, water, rust and any oil based products.
- The product consists of two parts; (PART A - Resin & PART B - Activator) (Ratio 2:1)
- Using a small trowel, mix 2 parts A and 1 part B. Mix the combined product thoroughly for at least 3-5 minutes.
- Apply the **GripEpoxy 116** with a steel trowel onto the wooden shutters
- Clean equipment and brushes with an Epoxy Cleaner
- Mixing should not take place in temperatures below 5°C. Do not apply to wet surfaces.

Caution:

Avoid contact with eyes and skin. In case of contact with eyes, immediately flush eyes with water and immediately call a physician. Wash hands after contact. Always wear dust masks when handling, mixing and applying products. Also refer to **MATERIAL SAFETY DATA SHEET**.



Stanton Construction Chemicals Pty (Ltd).

Unit 2A Veni View Park 547 Heritage View Drive
Muldersdrift, South Africa, 1735

Tel: +27 (0) 10 593-4454

Email: www.office.co.za

Website: www.sccsa.co.za



The information, and, in particular, the recommendations relating to the application and end-use of SCC products, are given in good faith based on SCC's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with SCC's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. SCC reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. Users must always refer to the most recent issue of the

Product Data Sheet for the product concerned, copies of which will be supplied on request. It may be necessary to adapt the above disclaimer to specific local laws and regulations. Any changes to this disclaimer may only be implemented with permission of SCC